

NAGGURA SKIN



The best skin for your treatment table



White
ngg 51



Graphite grey
ngg 52

ADVANCED VYNIL ARTIFICIAL LEATHER

ITEM REFERENCE	ngg51 (white) / ngg 52 (graphite grey)	
ABRASION RESISTANCE	>250.000 cycles (Martindale scale)	
TENSILE PROPERTIES	Tension load, warp-wise N/3cm	Standard=>120 Testing result 495
	Tension load, across-warp N/3cm	Standard=>70 Testing result 300
	Elongation at break, warp-wise %	Standard =>20 Testing result 93
	Elongation at break, across-warp %	Standard=>120 Testing result 165
TEARING STRENGTH N/3cm	Warp-Wise N	Standard=>10 Testing result 38
	Across warp N	Standard=>9 Testing result 28
PEEL STRENGTH	Warp-Wise N	Standard=>10 Testing result 14
COLD TOLERANCE	Cold crack resistance (-23°C, 5 min.)	
FLAME RETARDANT	NF P 92-503/M2 (non-flammable)	

DAILY CARE & CLEANING

* Clean at least once a week to maintain the coating clean and prevent accumulation of dirt and contaminants. This will extend the lifespan of your upholstery

* Clean the entire surface using neutral PH liquid soap and water in circular motions. To do so, use a white clean cloth soaked in the cleansing solution and wring out the wet cloth until all water is removed.

*Dry the surface using a white and clean cloth.

*Never use solvents, detergents and/or cleaning products that are not pH neutral.

*Never use cleaning tools made of plastic, abrasive sponges or hard-bristle brushes.